

CHO-SHIELD 579®

LOW VOC SILVER EPOXY COATING

DESCRIPTION

CHO-SHIELD® 579 coating is a two component, silver-filled, highly conductive epoxy paint designed to provide EMI shielding when applied to a dielectric substrate. This coating was specifically developed as a variant of CHO-SHIELD 596 with a lower VOC rating.

CHO-SHIELD 579 dries to the touch in less than 1 hour at room temperature and attains full chemical resistance after 1 week at room temperature. However, the best electrical properties are achieved by curing at elevated temperatures.

PERFORMANCE

CHO-SHIELD 579 has a VOC rating of 357 grams per liter.

CURE SCHEDULES

1. 1 hour at RT (75°F) and 1 hour at 150°F, followed by 1 hour at 250°F (recommended), or
2. 1 hour at 75°F and 1 hour at 250°F, or
3. 1 hour at 75°F and 6 hours at 150°F, or
4. 1 hour at room temperature followed by 4 hours at 175°F



Nominal Specific Gravity	1.80
Volume Resistivity*	0.06 ohm/sq.
Spray Viscosity (No. 2 Zahn Cup)	18 – 24 seconds
Pot Life at 24°C (75°F)	8 hours
Shelf Life at 24°C (7°F)	9 months
Theoretical Yield	7200 in ² /lb.

(* Based on a 1 hour room temperature drying period followed by 1 hour at 250°F (121°C) cure.

ORDERING INFORMATION

Product	Part Number	Unit Size
CHO-SHIELD 579	52-01-0579-0000	1 lb. (454 g)

APPLICATION INSTRUCTIONS

Mix parts A and B in the ratio of 100 parts of A to 32.09 parts of B by weight.

Apply the coating with an air gun such as a DeVilbiss Model EGA 502 with a 66SA air nozzle and 395 fluid nozzle. The spray viscosity range is typically 15 seconds (No. 2 Zahn Cup). The paint should be ready to use as mixed. Note: While the coating can be thinned as required with a mixture of 1 part methyl ethyl ketone (MEK) and 1 part toluene, "over-thinning" degrades electrical performance. Consult Chomerics Applications Department for assistance as required.

Apply the coating to a .6 to 1.0 mil thickness. (A wet film of 2 mils is approximately 1 mil when dry.) A 30-minute solvent flash is required between coats. The last coat should dry at room temperature for at least one hour prior to any elevated cure.

 **WARNING – USER RESPONSIBILITY**

FAILURE OR IMPROPER SELECTION OR IMPROPER USE OF THE PRODUCTS DESCRIBED HEREIN OR RELATED ITEMS CAN CAUSE DEATH, PERSONAL INJURY AND PROPERTY DAMAGE.

This document and other information from Parker-Hannifin Corporation, its subsidiaries and authorized distributors provide product or system options for further investigation by users having technical expertise.

The user, through its own analysis and testing, is solely responsible for making the final selection of the system and components and assuring that all performance, endurance, maintenance, safety and warning requirements of the application are met. The user must analyze all aspects of the application, follow applicable industry standards, and follow the information concerning the product in the current product catalog and in any other materials provided from Parker or its subsidiaries or authorized distributors.

To the extent that Parker or its subsidiaries or authorized distributors provide component or system options based upon data or specifications provided by the user, the user is responsible for determining that such data and specifications are suitable and sufficient for all applications and reasonably foreseeable uses of the components or systems.

OFFER OF SALE

The items described in this document are hereby offered for sale by Parker-Hannifin Corporation, its subsidiaries or its authorized distributors. This offer and its acceptance are governed by the provisions stated in the detailed "Offer of Sale" elsewhere in this document or available at: <http://www.chomerics.com/salesterms>